

TIKI ANTI-STRIPPING AGENT



Since 1964

For Use with Bitumen Binder for Promoting

No. 11-1511/A

DESCRIPTION

TIKI ANTI-STRIPPING AGENT-DS is specially formulated single component anti-stripping additive in paste form, used for bitumen binder as adhesion promoter ensuring better bonding of bitumen binder and improved quality of bituminous mix, thereby increasing the lifespan of bituminous pavements.

TIKI ANTI-STRIPPING AGENT-DS is unique anti-stripping agent based on specialty processed fatty organic amine base, which when added to bitumen binder improves the mixing and compaction of bituminous mix.

TIKI ANTI-STRIPPING AGENT-DS is a lipophilic surfactant, which is insoluble alone in water but dispersible in hot water to form a milky emulsion. It can be solubilized in water, if an organic or mineral acid (formic acid, acetic acid, hydrochloric acid, etc.) is added.

As **TIKI ANTI-STRIPPING AGENT-DS** is supplied in paste form (semi-solid), it is recommended to heat it above its melting point for use as homogeneous liquid.

PROPERTIES

Appearance @25°C	Paste
Specific Gravity @50°C	>0.80
Viscosity @50°C	>10 cst
Water Content % by Volume	<1.0
Iodine Value	30 to 50g/100g
Total Alkalinity	5.5 to 6.5 ml HCL(N) / g
Cloud Point	>35°C
Solidification Point	<30°C
Flash Point	>180°C

AREAS OF APPLICATION

As **TIKI ANTI-STRIPPING AGENT-DS** is water insoluble, it is added to hot bitumen binder. The modified hot bitumen binder than would be used directly in hot mix applications or are further processed to produce emulsions, cutbacks, formulations etc., for cold mix applications

TIKI ANTI-STRIPPING AGENT-DS is also used as emulsifier for cationic bitumen emulsions such as rapid setting emulsions for use in surface dressings and tack coat, and medium setting emulsions for use in open graded mixes.

DOSAGE

Use of 0.25 to 2% of **TIKI ANTI-STRIPPING AGENT-DS** is recommended by weight of Bitumen.

Disclaimer: **TIKI TAR INDUSTRIES** Warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. While **TIKI TAR** endeavors to ensure that information given herein is correct to the best of our knowledge, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

We recommend that adequate tests be performed by you to determine if this product meet all of your requirements.

Note: Properties subject to change as per specific requirement.

Ver. 052026

